



1. Product description

KEIM Fixativ is a binder, thinner and fixing agent made from pure, liquid potassium silicate for KEIM's ultra long-life mineral paints.

2. Field of application

KEIM Fixativ is used as binder and dilution for the pure silicate-based, two-component paint systems, KEIM Purkristalat and KEIM Décor Paints. For KEIM Unikristalat it is used as dilution.

KEIM Fixativ may also be used as dilution for the KEIM Granital and KEIM Quarzil and systems.

Diluted KEIM Fixativ can be used to control or reduce the absorbency as a primer for highly absorbent mineral substrates.

Consolidation of sanding or dusting mineral substrates can be fixed.

3. Product properties

KEIM Fixativ bonds permanently with the substrate, is highly water vapor permeable, extremely resistant to weathering and absolutely incombustible. KEIM Fixativ contains no organic additives.

- Bonds permanently with the substrate by silicification
- Extremely weather-resistant
- Non-film-forming
- Extremely water vapor permeable
- High binding power
- Fixing action
- Non-flammable
- Absolutely UV-resistant
- Hinders fungal and mold growth

- Resistant to industrial fumes
- Solvent-resistant
- Environmentally friendly, good environmental impact assessment
- Excellent low environmental impact building material

Material characteristics

Specific weight: approx. 1.17 g/cm³
pH-value: approx. 11.3

Color shade

Yellow, clear

4. Application instructions

Substrate preparation

The mineral substrate must be sound, dry, clean and free of dust and grease.

Application

For pre-treating highly absorbent and/or sanding substrates:

Apply KEIM Fixativ, diluted 1:1 or 1:2 with water, with a brush.

For mixing with KEIM Purkristalat or KEIM Décor Paints:

Soak 5 kg of color powder in 4 liters of KEIM Fixativ.

For diluting KEIM Purkristalat, KEIM Décor Paints, KEIM Unikristalat, KEIM Granital or KEIM Quarzil:

See relevant Technical Data Sheet.

Working conditions

Air and surface temperature > 5 °C (> 41 ° F)



Drying times

A drying time of at least 12 hours must be allowed between pretreatment and priming and between coats.

Consumption

For pretreatment on a smooth substrate per m² (10.8 sq ft):

approx. 0.1 l (3.4 fl oz) KEIM Fixativ and

approx. 0.1 l (3.4 fl oz) water

The stated consumption value is for guidance and depends on the absorbency and texture of the substrate. Exact consumption values can only be determined by painting trial areas on the structure to be coated.

Cleaning of tools

Clean with water immediately after use.

5. Packaging

4 l and 24 l (1.1 and 6.3 gal) containers

6. Storage

Shelf life is approx. 12 months in a sealed container under cool, frost-free conditions. Protect from heat and direct sunlight.

7. Hazardous substances ordinance class

n/a

8. Transport hazard class

n/a

9. Disposal

EC Waste Code no. 06 02 99

Any residues must be emptied out of containers before recycling.

10. Safety instructions

KEIM Fixativ is alkaline. Provide appropriate protection for surfaces which are not to be coated (e.g. glass, natural stone, ceramics etc.). Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water. Protect the eyes and skin from splashes. Keep out of reach of children.

Product code: M-SK 02

The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release those purchasing and applying our products from the duty of establishing for themselves, with due care, the suitability of our products for the intended application. Standard building industry practices must be complied with. We retain the right to make modifications to improve the products or their application. This edition supersedes all earlier editions.

